

PATENT ABSTRACTS OF JAPAN

(11) Publication number: **03192132 A**

(43) Date of publication of application: **22.08.91**

(51) Int. Cl

**C08J 9/00**  
**B29C 67/20**  
**C08L 23/08**  
**C08L 23/16**  
**C08L 75/04**  
**// B29K105:04**  
**B29L 7:00**

(21) Application number: **01331838**

(22) Date of filing: **21.12.89**

(71) Applicant: **TONEN CHEM CORP**

(72) Inventor: **KAGAWA SEIJI**

**(54) PRODUCTION OF MICROPOROUS ELASTOMER FILM**

**(57) Abstract:**

**PURPOSE:** To produce a microporous film improved in waterproofness and gas transmissive property by feeding a film comprising a thermoplastic elastomer composition to the space between a heating roll and an elastic roll in such a way that a specified (non)woven fabric is applied to the film on the side of the heating roll and heating it under pressure.

**CONSTITUTION:** A thermoplastic elastomer composition

comprising, for example, 30-70wt.% ethylene/vinyl acetate copolymer and 70-30wt.% ethylene/propylene/diene copolymer or polyurethane elastomer is kneaded and molded to obtain a film of a thickness of 10-40 $\mu$ m. This film is fed to the space between a heating roll heated to 100°C or below and an elastic roll at a feed rate of 2-30m/min in such a way that a (non)woven fabric containing 40-200cc/m<sup>2</sup> of a mixture of water with optionally an alcohol is applied to the film on the side of the heating roll and heated to 100°C or higher under a pressure of 0.1-5kg/cm<sup>2</sup> to obtain the title film.

**COPYRIGHT:** (C)1991,JPO&Japio